

LATI Latamid 66 MDT03-01 PA 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Polyamide 66 (PA66) based compound. Magnetic detectable filler. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latamid-66-MDT03-01-PA-66.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	
Linear Mold Shrinkage, Flow	0.0060 - 0.010 cm/cm	0.0060 - 0.010 in/in	
Linear Mold Shrinkage, Transverse	0.0060 - 0.010 cm/cm	0.0060 - 0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa @Temperature 23.0 Â°C	8700 psi @Temperature 73.4 Â°F	
Elongation at Break	18 % @Temperature 23.0 Â°C	18 % @Temperature 73.4 Â°F	
Elongation at Yield	12 %	12 %	
Tensile Modulus	2.85 GPa @Temperature 23.0 Â°C	413 ksi @Temperature 73.4 Â°F	
Charpy Impact Unnotched	10.0 J/cm ²	47.6 ft-lb/in ²	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 Â°C	482 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	230 Â°C	446 Â°F	
Vicat Softening Point	250 Â°C @Load 5.00 kg	482 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric ^{90 Å°C}	English ^{194 Å°F}	Comments
Mold Temperature	80.0 - 100 Å°C	176 - 212 Å°F	
Drying Temperature	90.0 - 100 Å°C @Time 10800 sec	194 - 212 Å°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China