

LATI Latan 13 G/30 POM, 30% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, 30% Glass Fiber Reinforced

Material Notes:

Polyoxymethylene (POM) based compound. Glass fibers. Medium viscosity. Good tribological properties. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latan-13-G30-POM-30-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.59 g/cc	0.0574 lb/in ³	
Linear Mold Shrinkage, Flow	0.0045 - 0.0070 cm/cm	0.0045 - 0.0070 in/in	
Linear Mold Shrinkage, Transverse	0.011 - 0.014 cm/cm	0.011 - 0.014 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	
	@Temperature 90.0 °C	@Temperature 194 °F	
	85.0 MPa	12300 psi	
	@Temperature 60.0 °C	@Temperature 140 °F	
	100 MPa	14500 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Elongation at Break	3.0 %	3.0 %	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	4.0 %	4.0 %	
	@Temperature 60.0 °C	@Temperature 140 °F	
	5.8 %	5.8 %	
	@Temperature 90.0 °C	@Temperature 194 °F	
Tensile Modulus	4.00 GPa	580 ksi	
	@Temperature 90.0 °C	@Temperature 194 °F	
	5.90 GPa	856 ksi	

Mechanical Properties	Metric	English	Comments
	7.50 GPa @Temperature 60.0 Å°C	1090 ksi @Temperature 140 Å°F	
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Charpy Impact Unnotched	2.50 J/cmÅ² @Temperature 23.0 Å°C	11.9 ft-lb/inÅ² @Temperature 73.4 Å°F	
Charpy Impact, Notched	0.500 J/cmÅ² @Temperature 23.0 Å°C	2.38 ft-lb/inÅ² @Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	85.0 Å°C	185 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	165 Å°C	329 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	160 Å°C	320 Å°F	
Vicat Softening Point	150 Å°C @Load 5.00 kg	302 Å°F @Load 11.0 lb	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 210 Å°C	356 - 410 Å°F	
Mold Temperature	80.0 - 100 Å°C	176 - 212 Å°F	
Drying Temperature	80.0 - 90.0 Å°C @Time 10800 sec	176 - 194 Å°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China