

LATI Latilub 66-20T PA66, PTFE Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, PTFE Filled

Material Notes:

Self-lubricating product based on Polyamide 66 (PA66). PTFE. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latilub-66-20T-PA66-PTFE-Filled.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	
Linear Mold Shrinkage, Flow	0.013 - 0.016 cm/cm	0.013 - 0.016 in/in	
Linear Mold Shrinkage, Transverse	0.014 - 0.017 cm/cm	0.014 - 0.017 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	
Elongation at Break	10 %	10 %	
Elongation at Yield	9.0 %	9.0 %	
Tensile Modulus	2.80 GPa	406 ksi	
Charpy Impact Unnotched	5.50 J/cm ²	26.2 ft-lb/in ²	
Charpy Impact, Notched	0.280 J/cm ²	1.33 ft-lb/in ²	
Coefficient of Friction, Dynamic	0.22	0.22	
Coefficient of Friction, Static	0.26	0.26	
K (wear) Factor	6.20 x 10 ⁻⁸ mm ³ /N-M	3.08 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 Â°C	482 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	100 Â°C	212 Â°F	
Vicat Softening Point	245 Â°C @Load 5.00 kg	473 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	270 - 300 Â°C Metric	518 - 572 Â°F English	Comments
Mold Temperature	70.0 - 90.0 Â°C	158 - 194 Â°F	
Drying Temperature	90.0 - 100 Â°C @Time 10800 sec	194 - 212 Â°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China