

LATI Latilub 87/28-15T K/20 PC, 20% Carbon Fiber Reinforced, PTFE Filled

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon + PTFE Filled

Material Notes:

Self-lubricating product based on Polycarbonate (PC). PTFE. Carbon fiber. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latilub-8728-15T-K20-PC-20-Carbon-Fiber-Reinforced-PTFE-Filled.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	
Linear Mold Shrinkage, Flow	0.0015 - 0.0025 cm/cm	0.0015 - 0.0025 in/in	
Linear Mold Shrinkage, Transverse	0.0025 - 0.0040 cm/cm	0.0025 - 0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	
Elongation at Break	1.5 %	1.5 %	
Tensile Modulus	15.3 GPa	2220 ksi	
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	
Coefficient of Friction, Dynamic	0.17	0.17	
Coefficient of Friction, Static	0.24	0.24	
K (wear) Factor	9.00 x 10 ⁻⁸ mm ³ /N-M	4.47 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	145 Â°C	293 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	140 Â°C	284 Â°F	
Vicat Softening Point	150 Â°C @Load 5.00 kg	302 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	275 - 320 Â°C	527 - 608 Â°F	

Mold Temperature Processing Properties	80.0 - 110 Å°C Metric	175 - 230 Å°F English	Comments
Drying Temperature	110 - 130 Å°C @Time 10800 sec	230 - 266 Å°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China