

LATI Latimass 82-03 D080 PA12

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Specific density compound based on Polyamide 12 (PA12). Special filler. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latimass-82-03-D080-PA12.php

Physical Properties	Metric	English	Comments
Density	8.10 g/cc	0.293 lb/in ³	
Linear Mold Shrinkage, Flow	0.0055 - 0.0085 cm/cm	0.0055 - 0.0085 in/in	
Linear Mold Shrinkage, Transverse	0.0055 - 0.0085 cm/cm	0.0055 - 0.0085 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	
Elongation at Break	1.3 %	1.3 %	
Tensile Modulus	4.80 GPa	696 ksi	
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	155 Â°C	311 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	100 Â°C	212 Â°F	
Vicat Softening Point	165 Â°C @Load 5.00 kg	329 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 Â°C	482 - 518 Â°F	
Mold Temperature	70.0 - 90.0 Â°C	158 - 194 Â°F	
Drying Temperature	80.0 - 100 Â°C @Time 10800 sec	176 - 212 Â°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China