

## LG Chemical 15NFE GPPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Molded, Unreinforced

### Material Notes:

High flow, Superior transparency and processability, good appearance, non-toxicity (Conforming to FDA CFR 177.1640), Excellent electrical properties, Heat resistance and chemical resistance, Superior extrusion processing suitable for OPS, PSP and synthetic wood, Applications include transparent receptacles for medicines and food, toys, goods, audio tapes, stationery, fans, food receptacles, disposable cups, PSP sheet, and film

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-15NFE-GPPS.php](http://www.lookpolymers.com/polymer_LG-Chemical-15NFE-GPPS.php)

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	6.8 g/10 min @Load 5.00 kg, Temperature 200 °C	6.8 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	47.1 MPa	6830 psi	50 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	50 mm/min; ASTM D638
Flexural Yield Strength	91.3 MPa	13200 psi	15 mm/min; ASTM D790
Flexural Modulus	3.10 GPa	450 ksi	15 mm/min; ASTM D790

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C @Thickness 12.7 mm	185 °F @Thickness 0.500 in	Unannealed; ASTM D648
Flammability, UL94	HB	HB	1/16 in
	HB	HB	1/8 in
Flame Spread	28.0 mm/min @Thickness 3.17 mm	1.10 in/min @Thickness 0.125 in	FH3

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Optical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China