

## LG Chemical KEYFLEX BT 1172D Ester Type TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester, TP , Polyester Thermoplastic Elastomer

### Material Notes:

Description: Injection Molding, TPC-ET, General Purpose, High Modulus  
 Application: Cable & Wire Jackets, Hose & Tubing, Sheet  
 CAS: 37282-12-5  
 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-KEYFLEX-BT-1172D-Ester-Type-TPE.php](http://www.lookpolymers.com/polymer_LG-Chemical-KEYFLEX-BT-1172D-Ester-Type-TPE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Water Absorption	0.30 % @Temperature 23.0 Â°C, Time 86400 sec	0.30 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Molecular Weight	458.458 g/mol	458.458 g/mol	
Maximum Moisture Content	0.010	0.010	Injection Molding
	0.010	0.010	Extrusion Molding
Linear Mold Shrinkage, Flow	0.015 - 0.019 cm/cm @Thickness 3.20 mm	0.015 - 0.019 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	14 g/10 min @Load 2.16 kg, Temperature 240 Â°C	14 g/10 min @Load 4.76 lb, Temperature 464 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	66	66	ASTM D2240
Tensile Strength at Break	45.1 MPa @Thickness 2.00 mm	6540 psi @Thickness 0.0787 in	50mm/min; ASTM D638
Elongation at Break	400 % @Thickness 2.00 mm	400 % @Thickness 0.0787 in	50mm/min; ASTM D638
Flexural Modulus	0.471 GPa @Thickness 6.40 mm	68.3 ksi @Thickness 0.252 in	15mm/min; ASTM D790
Izod Impact, Notched	0.490 J/cm @Thickness 6.40 mm, Temperature -40.0 Â°C	0.918 ft-lb/in @Thickness 0.252 in, Temperature -40.0 Â°F	ASTM D256

Mechanical Properties	1.47 J/cm Metric	2.76 ft-lb/in English	Comments ASTM D256
	@Thickness 6.40 mm, Temperature 23.0 Â°C	@Thickness 0.252 in, Temperature 73.4 Â°F	
Tear Strength	162 kN/m	924 pli	50mm/min, at Break; ASTM D624

Thermal Properties	Metric	English	Comments
Melting Point	217 Â°C	423 Â°F	Peak
Boiling Point	140 - 230 Â°C	284 - 446 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	130 Â°C @Thickness 6.40 mm	266 Â°F @Thickness 0.252 in	Unannealed; ASTM D648
UL RTI, Electrical	50.0 Â°C @Thickness >=1.50 mm	122 Â°F @Thickness >=0.0591 in	
	50.0 Â°C @Thickness >=3.00 mm	122 Â°F @Thickness >=0.118 in	
UL RTI, Mechanical with Impact	50.0 Â°C @Thickness >=1.50 mm	122 Â°F @Thickness >=0.0591 in	
	50.0 Â°C @Thickness >=3.00 mm	122 Â°F @Thickness >=0.118 in	
UL RTI, Mechanical without Impact	50.0 Â°C @Thickness >=1.50 mm	122 Â°F @Thickness >=0.0591 in	
	50.0 Â°C @Thickness >=3.00 mm	122 Â°F @Thickness >=0.118 in	
Flammability, UL94	HB @Thickness >=1.50 mm	HB @Thickness >=0.0591 in	
	HB @Thickness >=3.00 mm	HB @Thickness >=0.118 in	
Flash Point	300 - 340 Â°C	572 - 644 Â°F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	ASTM D257

Electrical Properties	25.0 kV/mm Metric	650 kV/in English	Comments
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Comparative Tracking Index	600 V	600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	Injection Molding
Middle Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	Injection Molding
Front Barrel Temperature	235 - 255 Â°C	455 - 491 Â°F	Injection Molding
Nozzle Temperature	235 - 255 Â°C	455 - 491 Â°F	Injection Molding
Zone 1	220 - 240 Â°C	428 - 464 Â°F	Extrusion Molding
Zone 2	225 - 245 Â°C	437 - 473 Â°F	Extrusion Molding
Zone 3	230 - 250 Â°C	446 - 482 Â°F	Extrusion Molding
Zone 4	235 - 245 Â°C	455 - 473 Â°F	Extrusion Molding
Adapter Temperature	235 - 245 Â°C	455 - 473 Â°F	Extrusion Molding
Die Temperature	220 - 260 Â°C	428 - 500 Â°F	Extrusion Molding
Melt Temperature	220 - 240 Â°C	428 - 464 Â°F	Injection Molding
	220 - 240 Â°C	428 - 464 Â°F	Extrusion Molding
Mold Temperature	40.0 - 60.0 Â°C	104 - 140 Â°F	Injection Molding
Drying Temperature	80.0 - 90.0 Â°C	176 - 194 Â°F	Injection Molding
	80.0 - 90.0 Â°C	176 - 194 Â°F	Extrusion Molding
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	Injection Molding
	3.00 - 4.00 hour	3.00 - 4.00 hour	Extrusion Molding

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China