

## LG Chemical LUPOL HM-4354 Heat Resistant Polypropylene, 35% Glass Fiber/Mineral Filler Reinforced, High Strength, High Modulus

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

### Material Notes:

LUPOL resins, based on polyolefin with a wide range of characteristics, are a family of low cost engineering plastics. Applications:

Automotive: Bumper cover, instrument panel, glove box, air cleaner, mud guard, door trim, garnish Electrical and Electronic: Tail lamp

housing, air conditioner housing, fan, socket, washing machine parts Industrial Parts and Household Appliance: Propeller fan, pulley,

container, pump container, pump casing, handle and switch cover of electric jar, fan shroud/support Information Provided by LG Chem

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-LUPOL-HM-4354-Heat-Resistant-Polypropylene-35-Glass-FiberMineral-Filler-Reinforced-High-Strength-High-Modulus.php](http://www.lookpolymers.com/polymer_LG-Chemical-LUPOL-HM-4354-Heat-Resistant-Polypropylene-35-Glass-FiberMineral-Filler-Reinforced-High-Strength-High-Modulus.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.0 MPa	6380 psi	ASTM D638
Elongation at Break	7.0 %	7.0 %	ASTM D638
Flexural Strength	77.0 MPa	11200 psi	ASTM D790
Flexural Modulus	4.20 GPa	609 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm @Temperature 23.0 Â°C	0.749 ft-lb/in @Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	134 Â°C	273 Â°F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	200 - 220 Â°C	392 - 428 Â°F	
Middle Barrel Temperature	200 - 230 Â°C	392 - 446 Â°F	
Front Barrel Temperature	210 - 230 Â°C	410 - 446 Â°F	
Nozzle Temperature	210 - 240 Â°C	410 - 464 Â°F	

Processing Properties	Metric $^{\circ}\text{C}$	English $^{\circ}\text{F}$	Comments
Mold Temperature	40.0 - 90.0 $^{\circ}\text{C}$	104 - 194 $^{\circ}\text{F}$	
Drying Temperature	70.0 - 90.0 $^{\circ}\text{C}$	158 - 194 $^{\circ}\text{F}$	
Dry Time	2 - 3 hour	2 - 3 hour	
Injection Pressure	29.4 - 118 MPa	4260 - 17100 psi	First
	78.45 - 98.07 MPa	11380 - 14220 psi	Second
Back Pressure	0.490 - 3.92 MPa	71.1 - 569 psi	
Screw Speed	40 - 60 rpm	40 - 60 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China