

LG Chemical LUPOS GP2300 ABS+GF30%, General Purpose

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Glass Fiber Filled

Material Notes:

Feature: Injection Molding, ABS+GF30%, General Purpose
 Application: Electric & Electronic (Housing, Components)
 CAS No. 9003-54-7, 9003-56-9 and 65997-17-3
 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUPOS-GP2300-ABSGF30-General-Purpose.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.28 g/cc	1.28 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm @Thickness 3.20 mm	0.0010 - 0.0020 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	2.3 g/10 min @Load 2.16 kg, Temperature 250 Å°C	2.3 g/10 min @Load 4.76 lb, Temperature 482 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	88.3 MPa @Thickness 3.20 mm	12800 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	3.0 % @Thickness 3.20 mm	3.0 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	142 MPa @Thickness 3.20 mm	20600 psi @Thickness 0.126 in	10mm/min; ASTM D790
Flexural Modulus	7.35 GPa @Thickness 3.20 mm	1070 ksi @Thickness 0.126 in	10mm/min; ASTM D790
Izod Impact, Notched	0.785 J/cm @Thickness 3.20 mm, Temperature 23.0 Å°C	1.47 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	99.0 Å°C @Thickness 6.40 mm	210 Å°F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	220 - 235 Â°C	428 - 455 Â°F	Injection Molding
Middle Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	Injection Molding
Front Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	Injection Molding
Nozzle Temperature	230 - 245 Â°C	446 - 473 Â°F	Injection Molding
Melt Temperature	235 - 245 Â°C	455 - 473 Â°F	Injection Molding
Mold Temperature	50.0 - 80.0 Â°C	122 - 176 Â°F	Injection Molding
Drying Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding
Back Pressure	0.981 - 3.92 MPa	142 - 569 psi	Injection Molding
Screw Speed	40 - 60 rpm	40 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China