

LG Chemical LUTENE XL8080UC PE Compound

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Description: LUTENE XL8080UC is a superior cleanliness version for high voltage power cable insulation and is designated as UC (Ultra-Clean) due to its extremely low level of contamination. LUTENE XL8080UC use a special base resin with lower melt index than well-known XL8080UC to prevent a sag in heavy walled cables. Applications: Extra high voltage power cable insulation CAS No: 9002-88-4 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUTENE-XL8080UC-PE-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.922 g/cc	0.922 g/cc	ISO 1183-D
Degree of Crosslinking	>= 80 %	>= 80 %	ASTM D2765A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 19.7 MPa	>= 2860 psi	ISO 527
	>= 18.72 MPa	>= 2715 psi	IEC 60811-1-2
	@Temperature 136 Â°C, Time 605000 sec	@Temperature 277 Â°F, Time 168 hour	
Elongation at Break	550 %	550 %	ISO 527
	522.5 %	522.5 %	IEC 60811-1-2
	@Temperature 136 Â°C, Time 605000 sec	@Temperature 277 Â°F, Time 168 hour	

Thermal Properties	Metric	English	Comments
Melting Point	120 - 130 Â°C	248 - 266 Â°F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Dielectric Constant	2.3	2.3	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	>= 24.0 kV/mm	>= 610 kV/in	IEC 60243
	0.0040	0.0040	

Electrical Properties	Metric	English	Comments
	@ Frequency 1.00e+6 Hz	@ Frequency 1.00e+6 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China