

LG Chemical Lupox[®] LW5402A PBT+PC+GF40%

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Glass Filled , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Description: Injection Molding, PBT+PC+GF40%, Low Warpage, High Gloss
Application: E&E, Automotive (Bobbin, Switch)
CAS No. 9010-86-0, 65997-17-3, 24968-12-5 and 103598-77-2
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-LW5402A-PBTPCGF40.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0030 - 0.0060 cm/cm @Thickness 3.20 mm	0.0030 - 0.0060 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	96.1 MPa @Thickness 3.20 mm	13900 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	6.0 % @Thickness 3.20 mm	6.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	152 MPa @Thickness 3.20 mm	22000 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	7.85 GPa @Thickness 3.20 mm	1140 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.735 J/cm @Thickness 3.20 mm, Temperature 23.0 °C	1.38 ft-lb/in @Thickness 0.126 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	@ Break; ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	210 °C @Thickness 6.40 mm	410 °F @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	195 °C @Thickness 6.40 mm	383 °F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	235 - 250 Â°C	455 - 482 Â°F	Injection Molding
Middle Barrel Temperature	240 - 250 Â°C	464 - 482 Â°F	Injection Molding
Front Barrel Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Nozzle Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Melt Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Mold Temperature	60.0 - 100 Â°C	140 - 212 Â°F	Injection Molding
Drying Temperature	120 Â°C	248 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China