

LG Chemical Lupox[®] PBT-GP-2150 15% GFR PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

Information provided by US distributor Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-PBT-GP-2150-15-GFR-PBT.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ASTM D792
Water Absorption	0.070 %	0.070 %	24 hours at 73 [°] F; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.011 cm/cm	0.0040 - 0.011 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Ultimate	93.1 MPa @Thickness 3.17 mm	13500 psi @Thickness 0.125 in	ASTM D638
Tensile Strength, Yield	93.1 MPa	13500 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	147 MPa	21300 psi	ASTM D570
Flexural Modulus	4.90 GPa	711 ksi	ASTM D570
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 [°] C	410 [°] F	ASTM D648
Flammability, UL94	HB @Thickness 0.7937 mm	HB @Thickness 0.03125 in	UL94

Electrical Properties	Metric	English	Comments
Arc Resistance	95 sec	95 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 245 [°] C	446 - 473 [°] F	

Processing Properties	Metric	English	Comments
Front Barrel Temperature	240 - 250 Â°C	464 - 482 Â°F	
Nozzle Temperature	240 - 260 Â°C	464 - 500 Â°F	
Melt Temperature	240 - 260 Â°C	464 - 500 Â°F	
Mold Temperature	50.0 - 100 Â°C	122 - 212 Â°F	Surface
Drying Temperature	120 Â°C	248 Â°F	5 hr.
	140 Â°C	284 Â°F	3 hr.
	120 Â°C	248 Â°F	
	@Time 18000 sec	@Time 5.00 hour	
	140 Â°C	284 Â°F	
	@Time 10800 sec	@Time 3.00 hour	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Shot Size	40 - 80 %	40 - 80 %	
Vent Depth	0.00254 - 0.00381 cm	0.00100 - 0.00150 in	

Descriptive Properties	Value	Comments
Ram Speed Setting	Medium to Fast	
Screw Speed	Medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China