

LG Chemical Lupox[®] SG3250 PBT+PET+MF25%

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET, Mineral Filled , Polyethylene Terephthalate (PET)

Material Notes:

Injection Molding, PBT+PET+MF25%, Good Surface Application: Automotive (Head Lamp Bezel) CAS No. 24968-12-5, 25038-59-9 and 14807-96-6 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-SG3250-PBTPETMF25.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.54 g/cc	1.54 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0050 - 0.012 cm/cm @Thickness 3.20 mm	0.0050 - 0.012 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	53.9 MPa @Thickness 3.20 mm	7820 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	3.0 % @Thickness 3.20 mm	3.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	93.2 MPa @Thickness 3.20 mm	13500 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	5.10 GPa @Thickness 3.20 mm	740 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.294 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	0.551 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	225 Â°C	437 Â°F	@ Break; ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	200 Â°C @Thickness 6.40 mm	392 Â°F @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	105 Â°C @Thickness 6.40 mm	221 Â°F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	235 - 250 Â°C	455 - 482 Â°F	Injection Molding
Middle Barrel Temperature	240 - 250 Â°C	464 - 482 Â°F	Injection Molding
Front Barrel Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Nozzle Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Melt Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Mold Temperature	60.0 - 100 Â°C	140 - 212 Â°F	Injection Molding
Drying Temperature	120 Â°C	248 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China