

LG Chemical Lupox[®] SG3250M PBT+PET+MF25%

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET, Mineral Filled , Polyethylene Terephthalate (PET)

Material Notes:

Description: Injection Molding, PBT+PET+MF25%, Good Surface Application: Automotive (Head Lamp Bezel) CAS No. 24968-12-5, 25038-59-9 and 14807-96-6 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-SG3250M-PBTPETMF25.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.54 g/cc	1.54 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0050 - 0.012 cm/cm @Thickness 3.20 mm	0.0050 - 0.012 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	44.1 MPa @Thickness 3.20 mm	6400 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	3.5 % @Thickness 3.20 mm	3.5 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	83.4 MPa @Thickness 3.20 mm	12100 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	4.31 GPa @Thickness 3.20 mm	626 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.294 J/cm @Thickness 3.20 mm, Temperature 23.0 °C	0.551 ft-lb/in @Thickness 0.126 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	@ Break; ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	200 °C @Thickness 6.40 mm	392 °F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Rear Barrel Temperature Processing Properties	245 - 255 Å°C Metric	473 - 491 Å°F English	Injection Molding Comments
Middle Barrel Temperature	250 - 260 Å°C	482 - 500 Å°F	Injection Molding
Front Barrel Temperature	255 - 265 Å°C	491 - 509 Å°F	Injection Molding
Nozzle Temperature	255 - 265 Å°C	491 - 509 Å°F	Injection Molding
Melt Temperature	255 - 265 Å°C	491 - 509 Å°F	Injection Molding
Mold Temperature	80.0 - 100 Å°C	176 - 212 Å°F	Injection Molding
Drying Temperature	120 Å°C	248 Å°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China