

## LG Chemical SEETEC BF415 LDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

### Material Notes:

Characteristics: Good Processability and Excellent Optical Properties Applications: Masking film CAS No. 9002-88-4 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-SEETEC-BF415-LDPE.php](http://www.lookpolymers.com/polymer_LG-Chemical-SEETEC-BF415-LDPE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.922 - 0.926 g/cc	0.922 - 0.926 g/cc	ASTM D1505
Melt Flow	1.6 - 2.0 g/10 min @Load 2.61 kg, Temperature 190 Â°C	1.6 - 2.0 g/10 min @Load 5.75 lb, Temperature 374 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	12.3 MPa	1780 psi	500mm/min; ASTM D638
Film Elongation at Break, MD	300 %	300 %	500 mm/min; ASTM D638
Film Elongation at Break, TD	550 %	550 %	500 mm/min; ASTM D638
Elongation at Break	550 %	550 %	500 mm/min; ASTM D638
2% Secant Modulus	1.20 GPa	174 ksi	500mm/min; ASTM D638
Elmendorf Tear Strength MD	400 g	400 g	ASTM D1922
Elmendorf Tear Strength TD	180 g	180 g	ASTM D1922
Dart Drop Test	55.0 g	0.121 lb	ASTM D1709
Film Tensile Strength at Break, MD	25.5 MPa	3700 psi	500mm/min, Ultimate; ASTM D638
Film Tensile Strength at Break, TD	23.5 MPa	3410 psi	500mm/min, Ultimate; ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	112 Â°C	234 Â°F	10Â°C/min; ASTM D3418
Vicat Softening Point	92.0 Â°C	198 Â°F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003
Gloss	95 %	95 %	45Â°; ASTM D2457

Optical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China