

LG Chemical SEETEC H7500 Polypropylene, Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Features: Seetec H7500 is designed for the extrusion of continuous filament (CF). This grade is characterized by medium MWD and good processability from specific additives. SEETEC H7500 meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520 for food contact. Applications: woven and knitted fabrics CAS No. 9003-07-0 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-SEETEC-H7500-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D1505
Melt Flow	15.05 g/10 min	15.05 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	34.3 MPa	4980 psi	50mm/min; ASTM D638
Elongation at Break	<= 500 %	<= 500 %	50mm/min; ASTM D638
Flexural Modulus	1.57 GPa	228 ksi	ASTM D760
Izod Impact, Notched	0.245 J/cm	0.459 ft-lb/in	ASTM D256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Melting Point	140 - 170 Â°C	284 - 338 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	106 Â°C	223 Â°F	ASTM D648
Vicat Softening Point	152 Â°C	306 Â°F	ASTM D1525
	@Load 1.00 kg	@Load 2.20 lb	
Flash Point	>= 340 Â°C	>= 644 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China