

## LG Chemical SEETEC M1500 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene, Impact Modified; Molded/Extruded

### Material Notes:

SEETEC M1500 is a heterophasic polypropylene copolymer for injection molding applications. SEETEC M1500 exhibits a high flowability and a good balance of stiffness and impact strength. SEETEC M1500 meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520 for food contact. Applications: Automotive Parts, Housewares CAS No. 9010-79-1 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-SEETEC-M1500-Polypropylene-Impact-Copolymer.php](http://www.lookpolymers.com/polymer_LG-Chemical-SEETEC-M1500-Polypropylene-Impact-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D1505
Melt Flow	16 g/10 min	16 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	26.5 MPa	3840 psi	50mm/min; ASTM D638
Elongation at Break	>= 300 %	>= 300 %	50mm/min; ASTM D638
Flexural Modulus	1.23 GPa	178 ksi	ASTM D760
Izod Impact, Notched	0.686 J/cm	1.29 ft-lb/in	ASTM D256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Melting Point	130 - 170 Â°C	266 - 338 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	105 Â°C	221 Â°F	ASTM D648
Vicat Softening Point	152 Â°C	306 Â°F	ASTM D1525
	@Load 1.00 kg	@Load 2.20 lb	
Flash Point	>= 340 Â°C	>= 644 Â°F	

Descriptive Properties	Value	Comments
Autoignition Temperature	>350Â°C	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**