

## LTL Color Compounds ColorFast<sup>®</sup> FRPBT200 PBT, Flame Retarded

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Flame Retardant

### Material Notes:

V-0 rated, unfilled PBT All information provided by LTL Color Compounds, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LTL-Color-Compounds-ColorFast-FRPBT200-PBT-Flame-Retarded.php](http://www.lookpolymers.com/polymer_LTL-Color-Compounds-ColorFast-FRPBT200-PBT-Flame-Retarded.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792
Linear Mold Shrinkage	0.015 - 0.023 cm/cm	0.015 - 0.023 in/in	0.125; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	58.6 MPa	8500 psi	2.0 in/min; ASTM D638
Tensile Strength, Yield	58.6 MPa	8500 psi	2.0 in/min; ASTM D638
Elongation at Break	80 %	80 %	2.0 in/min; ASTM D638
Flexural Strength	101 MPa	14700 psi	2.0 in/min; ASTM D790
Flexural Modulus	2.62 GPa	380 ksi	2.0 in/min; ASTM D790
Izod Impact, Notched	0.374 J/cm @Temperature 22.8 °C	0.700 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	71.1 °C	160 °F	Unannealed (0.250"); ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	232 - 249 °C	450 - 480 °F	
Middle Barrel Temperature	238 - 254 °C	460 - 490 °F	
Front Barrel Temperature	243 - 260 °C	470 - 500 °F	
Nozzle Temperature	238 - 254 °C	460 - 490 °F	
Melt Temperature	243 - 260 °C	470 - 500 °F	
Mold Temperature	48.9 - 76.7 °C	120 - 170 °F	

Processing Properties	Metric	English	Comments
Dry Time	3 - 4 hour	3 - 4 hour	nominal; maximum drying time of 12 hours
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Shot Size	40 - 60 %	40 - 60 %	
Vent Depth	0.00127 - 0.00254 cm	0.000500 - 0.00100 in	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China