

## LTL Color Compounds ColorFast® GPA300X ABS

Category : Polymer , Thermoplastic , ABS Polymer

### Material Notes:

Extrusion grade, high impact, high gloss ABS All information provided by LTL Color Compounds, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LTL-Color-Compounds-ColorFast-GPA300X-ABS.php](http://www.lookpolymers.com/polymer_LTL-Color-Compounds-ColorFast-GPA300X-ABS.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	0.125; ASTM D955
Melt Flow	7.0 g/10 min @Load 3.80 kg, Temperature 230 °C	7.0 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength at Break	27.6 MPa	4000 psi	2.0 in/min; ASTM D638
Tensile Strength, Yield	35.9 MPa	5200 psi	2.0 in/min; ASTM D638
Elongation at Break	110 %	110 %	2.0 in/min; ASTM D638
Elongation at Yield	3.0 %	3.0 %	2.0 in/min; ASTM D638
Flexural Strength	51.7 MPa	7500 psi	2.0 in/min; ASTM D790
Flexural Modulus	1.72 GPa	250 ksi	2.0 in/min; ASTM D790
Izod Impact, Notched	4.27 J/cm @Temperature 22.8 °C	8.00 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.8 °C	181 °F	Unannealed (0.250"); ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	188 - 210 °C	370 - 410 °F	
Middle Barrel Temperature	204 - 227 °C	400 - 440 °F	
Front Barrel Temperature	216 - 238 °C	420 - 460 °F	

<b>Nozzle Temperature Processing Properties</b>	<b>218 - 260 °C Metric</b>	<b>425 - 500 °F English</b>	<b>Comments</b>
Melt Temperature	218 - 260 °C	425 - 500 °F	
Mold Temperature	48.9 - 71.1 °C	120 - 160 °F	
Drying Temperature	82.2 - 93.3 °C	180 - 200 °F	
Dry Time	2 - 4 hour	2 - 4 hour	nominal; maximum drying time of 8 hours
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Shot Size	30 - 60 %	30 - 60 %	
Vent Depth	0.00381 - 0.00508 cm	0.00150 - 0.00200 in	
Screw Speed	30 - 60 rpm	30 - 60 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China