

LTL Color Compounds ColorFast[®] PBA2000 PBT/ABS Alloy, Flame Retarded

Category : Polymer , Thermoplastic , ABS Polymer , ABS/Polyester Alloy , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Flame-retarded V0-rated PBT/ABS alloy All information provided by LTL Color Compounds, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LTL-Color-Compounds-ColorFast-PBA2000-PBTABS-Alloy-Flame-Retarded.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	39.3 MPa	5700 psi	2.0 in/min; ASTM D638
Tensile Strength, Yield	21.4 MPa	3100 psi	2.0 in/min; ASTM D638
Elongation at Break	13 %	13 %	2.0 in/min; ASTM D638
Flexural Strength	68.9 MPa	10000 psi	2.0 in/min; ASTM D790
Flexural Modulus	2.21 GPa	320 ksi	2.0 in/min; ASTM D790
Izod Impact, Notched	0.534 J/cm @Temperature 22.8 Â°C	1.00 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0 @Thickness 1.30 mm	V-0 @Thickness 0.0512 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	204 - 238 Â°C	400 - 460 Â°F	
Middle Barrel Temperature	210 - 232 Â°C	410 - 450 Â°F	
Front Barrel Temperature	221 - 254 Â°C	430 - 490 Â°F	
Nozzle Temperature	216 - 249 Â°C	420 - 480 Â°F	
Melt Temperature	221 - 254 Â°C	430 - 490 Â°F	
Mold Temperature	10.0 - 71.1 Â°C	50.0 - 160 Â°F	
Drying Temperature	85.0 Â°C	185 Â°F	
	3 - 4 hour	3 - 4 hour	nominal; maximum drying time of 8

<small>Dry Time</small> Processing Properties	Metric	English	<small>Hours</small> Comments
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Shot Size	40 - 60 %	40 - 60 %	
Vent Depth	0.00254 - 0.00762 cm	0.00100 - 0.00300 in	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China