

## LTL Color Compounds ColorFast<sup>®</sup> PC200 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

20 melt superior processing, fast cycling All information provided by LTL Color Compounders, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LTL-Color-Compounds-ColorFast-PC200-Polycarbonate.php](http://www.lookpolymers.com/polymer_LTL-Color-Compounds-ColorFast-PC200-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	0.125; ASTM D955
Melt Flow	20 g/10 min @Load 1.20 kg, Temperature 300 Â°C	20 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Tensile Strength at Break	65.5 MPa	9500 psi	2.0 in/min; ASTM D638
Tensile Strength, Yield	62.1 MPa	9000 psi	2.0 in/min; ASTM D638
Elongation at Break	120 %	120 %	2.0 in/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	2.0 in/min; ASTM D638
Flexural Strength	93.1 MPa	13500 psi	2.0 in/min; ASTM D790
Flexural Modulus	2.31 GPa	335 ksi	2.0 in/min; ASTM D790
Izod Impact, Notched	6.41 J/cm @Temperature 22.8 Â°C	12.0 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	127 Â°C	260 Â°F	Unannealed (0.250"); ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 271 Â°C	480 - 520 Â°F	
Middle Barrel Temperature	260 - 282 Â°C	500 - 540 Â°F	
Front Barrel Temperature	271 - 293 Â°C	520 - 560 Â°F	

Processing Properties	Metric <b>88 Â°C</b>	English <b>10 Â°F</b>	Comments
Melt Temperature	271 - 293 Â°C	520 - 560 Â°F	
Mold Temperature	71.1 - 93.3 Â°C	160 - 200 Â°F	
Drying Temperature	121 Â°C	250 Â°F	
Dry Time	3 - 4 hour	3 - 4 hour	nominal; maximum drying time of 48 hours
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Shot Size	40 - 60 %	40 - 60 %	
Vent Depth	0.00254 - 0.00762 cm	0.00100 - 0.00300 in	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China