

Lanxess Durethan® DP 2131/20 H2.0 900051 Nylon 6, 20% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 20% Glass Fiber Filled

Material Notes:

PA 6, injection molding grade, 20% glass fibers, better surface resistance to alcoholic calcium chloride-solution than BKV 20 H2.0, good heat-ageing resistance and weather resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Durethan-DP-213120-H20-900051-Nylon-6-20-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ISO 1183
Viscosity Test	140 cm ³ /g	140 cm ³ /g	Viscosity number; ISO 307, 1157, 1628
Linear Mold Shrinkage, Flow	0.0035 cm/cm	0.0035 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0054 cm/cm	0.0054 in/in	ISO 294-4, 2577
Melt Flow	28 g/10 min @Load 5.00 kg, Temperature 270 °C	28 g/10 min @Load 11.0 lb, Temperature 518 °F	Estimated using room temperature density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
Tensile Modulus	7.30 GPa	1060 ksi	ISO 527-1/-2
Charpy Impact Unnotched	4.00 J/cm ² @Temperature -30.0 °C	19.0 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	4.00 J/cm ² @Temperature -30.0 °C	19.0 ft-lb/in ² @Temperature -22.0 °F	Conditioned; ISO 179/1eU
Charpy Impact Unnotched	4.50 J/cm ² @Temperature 23.0 °C	21.4 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
	6.00 J/cm ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	Conditioned; ISO 179/1eU
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA

Mechanical Properties	@Temperature -30.0 Metric °C	@Temperature -22.0 English °F	Comments
	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Puncture Energy	5.00 J	3.69 ft-lb	ISO 6603-2
	4.00 J	2.95 ft-lb	ISO 6603-2
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	4.00 J	2.95 ft-lb	Conditioned; ISO 6603-2
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	23.0 µm/m-°C	12.8 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	89.0 µm/m-°C	49.4 µin/in-°F	ISO 11359-1/-2
Melting Point	222 °C	432 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	213 °C	415 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	73.0 °C	163 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; IEC 60093
	3.00e+15 ohm-cm	3.00e+15 ohm-cm	IEC 60093
Surface Resistance	2.00e+13 ohm	2.00e+13 ohm	IEC 60093
Dielectric Constant	3.74	3.74	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	4.1	4.1	IEC 60250

Electrical Properties	Metric	English	Comments
	4.27	4.27	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	Conditioned; IEC 60250
	9.34	9.34	
	@Frequency 100 Hz	@Frequency 100 Hz	Conditioned; IEC 60250
Dissipation Factor	0.0087	0.0087	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0185	0.0185	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.0677	0.0677	Conditioned; IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.2203	0.2203	Conditioned; IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	

Descriptive Properties	Value	Comments
Additives	Release agent	
Features	Heat stabilized or stable to heat	
Form	Pellets	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China