

Lanxess Pocan® B 1505 000000 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Extrusion Grade , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

PBT, non-reinforced, injection molding, extrusion

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-B-1505-000000-PBT.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Water Absorption	0.50 %	0.50 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23 ^o C/50% R.H.; Test Sim. to ISO 62
Viscosity Test	140 cm ³ /g	140 cm ³ /g	Viscosity number; ISO 307, 1157, 1628
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 260 ^o C	20 g/10 min @Load 4.76 lb, Temperature 500 ^o F	Calculated from MVR using melt density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527-1/-2
Elongation at Break	20 %	20 %	Nominal; ISO 527-1/-2
Elongation at Yield	8.0 %	8.0 %	ISO 527-1/-2
Tensile Modulus	2.60 GPa	377 ksi	ISO 527-1/-2
Charpy Impact Unnotched	18.0 J/cm ²	85.7 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 ^o C	@Temperature -22.0 ^o F	
Charpy Impact, Notched	NB	NB	ISO 179/1eU
	@Temperature 23.0 ^o C	@Temperature 73.4 ^o F	
Charpy Impact, Notched	<= 1.00 J/cm ²	<= 4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 ^o C	@Temperature -22.0 ^o F	
Impact	<= 1.00 J/cm ²	<= 4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 ^o C	@Temperature 73.4 ^o F	
Impact	3650	3650	Puncture maximum force (N); ISO

Mechanical Properties	Metric	English	6603-2 Comments
	5191	5191	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Puncture maximum force (N); ISO 6603-2
Puncture Energy	22.0 J	16.2 ft-lb	ISO 6603-2
	32.0 J	23.6 ft-lb	
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 6603-2
Tensile Creep Modulus, 1 hour	2200 MPa	319000 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	1300 MPa	189000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	120 Âµm/m-Â°C	66.7 Âµin/in-Â°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	120 Âµm/m-Â°C	66.7 Âµin/in-Â°F	ISO 11359-1/-2
Melting Point	225 Â°C	437 Â°F	10Â°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	160 Â°C	320 Â°F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Â°C	140 Â°F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	45.0 Â°C	113 Â°F	ISO 75-1/-2
Vicat Softening Point	180 Â°C	356 Â°F	50Â°C/h 50N; ISO 306
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Oxygen Index	24 %	24 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.2	3.2	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
	3.4	3.4	

Electrical Properties	Metric @Frequency 100 Hz	English @Frequency 100 Hz	IEC 60250 Comments
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.0015 @Frequency 100 Hz	0.0015 @Frequency 100 Hz	IEC 60250
	0.019 @Frequency 1.00e+6 Hz	0.019 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 Â°C	500 Â°F	Injection Molding; ISO 294
Mold Temperature	80.0 Â°C	176 Â°F	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Additives	Lubricants	
	Release agent	
Features	Heat stabilized or stable to heat	
Form	Pellets	
ISO Shortname	ISO 7792-1-PBT,GHMR,11-030	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China