

## Lanxess Pocan® S 1506 901510 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Impact Grade , Polybutylene Terephthalate (PBT), Unreinforced, Molded

### Material Notes:

PBT, injection molding grade, non-reinforced, elastomer-modified, high impact strength, even at low temperatures

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lanxess-Pocan-S-1506-901510-PBT.php](http://www.lookpolymers.com/polymer_Lanxess-Pocan-S-1506-901510-PBT.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.40 %	0.40 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23 <sup>o</sup> C/50% R.H.; Test Sim. to ISO 62
Melt Flow	16 g/10 min @Load 5.00 kg, Temperature 260 <sup>o</sup> C	16 g/10 min @Load 11.0 lb, Temperature 500 <sup>o</sup> F	Estimated using room temperature density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.0 MPa	5080 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	Nominal; ISO 527-1/-2
Elongation at Yield	4.0 %	4.0 %	ISO 527-1/-2
Tensile Modulus	1.70 GPa	247 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 <sup>o</sup> C	@Temperature -22.0 <sup>o</sup> F	
Charpy Impact, Notched	NB	NB	ISO 179/1eA
	@Temperature 23.0 <sup>o</sup> C	@Temperature 73.4 <sup>o</sup> F	
Charpy Impact, Notched	2.50 J/cm <sup>2</sup>	11.9 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 <sup>o</sup> C	@Temperature -22.0 <sup>o</sup> F	
Charpy Impact, Notched	7.50 J/cm <sup>2</sup>	35.7 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 <sup>o</sup> C	@Temperature 73.4 <sup>o</sup> F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow			ISO 11359-1/-2

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	130 $\mu\text{m}/\text{m}\cdot\text{A}^\circ\text{C}$	72.2 $\mu\text{in}/\text{in}\cdot\text{A}^\circ\text{F}$	ISO 11359-1/-2
Melting Point	225 $\text{A}^\circ\text{C}$	437 $\text{A}^\circ\text{F}$	10 $\text{A}^\circ\text{C}/\text{min}$ ; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	100 $\text{A}^\circ\text{C}$	212 $\text{A}^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	55.0 $\text{A}^\circ\text{C}$	131 $\text{A}^\circ\text{F}$	ISO 75-1/-2
Vicat Softening Point	130 $\text{A}^\circ\text{C}$	266 $\text{A}^\circ\text{F}$	50 $\text{A}^\circ\text{C}/\text{h}$ 50N; ISO 306
Flammability, UL94	HB	HB	IEC 60695-11-10
	HB	HB	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Oxygen Index	22 %	22 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+15$ ohm-cm	$\geq 1.00\text{e}+15$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	IEC 60093
Dielectric Constant	3.1	3.1	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.2	3.2	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.0020	0.0020	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.017	0.017	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 $\text{A}^\circ\text{C}$	500 $\text{A}^\circ\text{F}$	Injection Molding; ISO 294
Mold Temperature	80.0 $\text{A}^\circ\text{C}$	176 $\text{A}^\circ\text{F}$	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Additives	Release agent	
Features	High impact or high impact modified	
Form	Pellets	
ISO Shortname	ISO 7792-PBT-I,MHR,11-020	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China