

Lanxess Pocan® S 7926 000000 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Extrusion Grade , Polybutylene Terephthalate (PBT), Flame Retardant , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

PBT, non-reinforced, injection molding, extrusion, flame retardant, impact modified

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-S-7926-000000-PBT.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	0.40 %	0.40 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C/50% R.H.; Test Sim. to ISO 62
Linear Mold Shrinkage, Flow	0.0019 cm/cm	0.0019 in/in	ISO 294-4, 2577
Linear Mold Shrinkage, Transverse	0.0019 cm/cm	0.0019 in/in	ISO 294-4, 2577
Melt Flow	41 g/10 min @Load 5.00 kg, Temperature 270 °C	41 g/10 min @Load 11.0 lb, Temperature 518 °F	Calculated from MVR using melt density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	ISO 527-1/-2
Elongation at Break	10 %	10 %	Nominal; ISO 527-1/-2
Elongation at Yield	3.0 %	3.0 %	ISO 527-1/-2
Tensile Modulus	2.40 GPa	348 ksi	ISO 527-1/-2
Charpy Impact Unnotched	16.0 J/cm ² @Temperature -30.0 °C	76.1 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	<= 1.00 J/cm ² @Temperature -30.0 °C	<= 4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	1.20 J/cm ² @Temperature 23.0 °C	5.71 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Mechanical Properties, 1 hour	Metric MPa	English psi	Comments
Tensile Creep Modulus, 1000 hours	1500 MPa	218000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	110 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	61.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-1/-2
CTE, linear, Transverse to Flow	120 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	66.7 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-1/-2
Melting Point	225 $\text{Å}^\circ\text{C}$	437 $\text{Å}^\circ\text{F}$	10 $\text{Å}^\circ\text{C}/\text{min}$; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	135 $\text{Å}^\circ\text{C}$	275 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	55.0 $\text{Å}^\circ\text{C}$	131 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	47.0 $\text{Å}^\circ\text{C}$	117 $\text{Å}^\circ\text{F}$	ISO 75-1/-2
Vicat Softening Point	165 $\text{Å}^\circ\text{C}$	329 $\text{Å}^\circ\text{F}$	50 $\text{Å}^\circ\text{C}/\text{h}$ 50N; ISO 306
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	IEC 60695-11-10
Oxygen Index	30 %	30 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+15$ ohm-cm	$\geq 1.00\text{e}+15$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	IEC 60093
Dielectric Constant	3.1 @Frequency 1.00e+6 Hz	3.1 @Frequency 1.00e+6 Hz	IEC 60250
	3.2 @Frequency 100 Hz	3.2 @Frequency 100 Hz	IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.0015 @Frequency 100 Hz	0.0015 @Frequency 100 Hz	IEC 60250
	0.015 @Frequency 1.00e+6 Hz	0.015 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	250 Â°C	482 Â°F	Injection Molding; ISO 294
Mold Temperature	80.0 Â°C	176 Â°F	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Additives	Flame retarding agent	
Features	Flame retardant	
Form	Pellets	
ISO Shortname	ISO 7792-1-PBT,GFHMPPR,11-020; ISO 1043-PBT FR(17)	
Processing	Injection molding	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China