

Lanxess Pocan® T 7391 POS151 900044 PBT + PET, 45% Glass Fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET Blend, Glass Filled , Polyethylene Terephthalate (PET)

Material Notes:

PBT + PET, 45% glass fibers, injection molding, improved surface finish, increased temperature peak load UV stabilized Information provided by LANXESS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-T-7391-POS151-900044-PBT-PET-45-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.69 g/cc	1.69 g/cc	ISO 1183
Bulk Density	0.800 g/cc	0.0289 lb/in ³	ISO 60
Moisture Absorption at Equilibrium	0.10 %	0.10 %	50% RH; ISO 62
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Viscosity Test	80 cm ³ /g	80 cm ³ /g	Viscosity number; ISO 1628-5
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	Post-shrinkage, 60x60x2; 120 ^o C; 4 hour; ISO 294-4
	0.0020 cm/cm	0.0020 in/in	60x60x2; 270 ^o C / MT 90 ^o C; 600 bar; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0010 cm/cm	0.0010 in/in	Post-shrinkage, 60x60x2; 120 ^o C; 4 hour; ISO 294-4
	0.0080 cm/cm	0.0080 in/in	60x60x2; 270 ^o C / MT 90 ^o C; 600 bar; ISO 294-4
Melt Flow	30 g/10 min	30 g/10 min	ISO 1133-1
	@Load 5.00 kg, Temperature 260 ^o C	@Load 11.0 lb, Temperature 500 ^o F	

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	250 MPa	36300 psi	ISO 2039-1
Tensile Strength at Break	160 MPa	23200 psi	ISO 527-1, -2; 5 mm/min
Elongation at Break	1.9 %	1.9 %	ISO 527-1, -2; 5 mm/min
Tensile Modulus	16.0 GPa	2320 ksi	ISO 527-1, -2; 1 mm/min
Flexural Strength	260 MPa	37700 psi	2 mm/min; ISO 178-A
	@Strain 2.10 %	@Strain 2.10 %	
Flexural Modulus	15.5 GPa	2250 ksi	2 mm/min; ISO 178-A

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	10.0 kJ/m ² @Temperature 23.0 °C	ft-lb/in ² @Temperature 73.4 °F	ISO 180-1A
	<= 10.0 kJ/m ² @Temperature -30.0 °C	<= 4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 180-1A
Izod Impact, Unnotched (ISO)	55.0 kJ/m ² @Temperature -30.0 °C	26.2 ft-lb/in ² @Temperature -22.0 °F	ISO 180-1U
	60.0 kJ/m ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 180-1U
Charpy Impact Unnotched	6.00 J/cm ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 179-1eU
	6.50 J/cm ² @Temperature -30.0 °C	30.9 ft-lb/in ² @Temperature -22.0 °F	ISO 179-1eU
Charpy Impact, Notched	<= 1.00 J/cm ² @Temperature -30.0 °C	<= 4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 179-1eA
	<= 1.00 J/cm ² @Temperature 23.0 °C	<= 4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 179-1eA
Tensile Creep Modulus, 1 hour	16500 MPa	2.39e+6 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	15000 MPa	2.18e+6 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 μm/m-°C @Temperature 23.0 - 55.0 °C	11.1 μin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-1, -2
CTE, linear, Transverse to Flow	80.0 μm/m-°C @Temperature 23.0 - 55.0 °C	44.4 μin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-1, -2
Thermal Conductivity	0.270 W/m-K	1.87 BTU-in/hr-ft ² - °F	ISO 8302
Melting Point	225 - 250 °C	437 - 482 °F	10°C/min; ISO 11357-1, -3

Thermal Properties	Metric	English	Comments
Temperature, Air	155 Â°C	311 Â°F	IEC 60216-1, Tensile impact strength, 20000 h
	155 Â°C	311 Â°F	IEC 60216-1, Electric strength, 20000 h
	220 Â°C	428 Â°F	Resistance to heat - ball pressure test; IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	225 Â°C	437 Â°F	ISO 75-1, -2
Deflection Temperature at 1.8 MPa (264 psi)	205 Â°C	401 Â°F	ISO 75-1, -2
Deflection Temperature at 8.0 MPa	150 Â°C	302 Â°F	ISO 75-1, -2
Vicat Softening Point	210 Â°C @Load 5.10 kg	410 Â°F @Load 11.2 lb	120Â°C/hour; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	
Oxygen Index	21 %	21 %	Method A; ISO 4589-2
Glow Wire Test	750 Â°C @Diameter 2.00 mm	1380 Â°F @Diameter 0.0787 in	GWFI; IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	4.2 @Frequency 1.00e+6 Hz	4.2 @Frequency 1.00e+6 Hz	IEC 60250
	4.3 @Frequency 100 Hz	4.3 @Frequency 100 Hz	IEC 60250
Dielectric Strength	28.0 kV/mm @Thickness 1.00 mm	711 kV/in @Thickness 0.0394 in	IEC 60243-1
Dissipation Factor	0.0020 @Frequency 100 Hz	0.0020 @Frequency 100 Hz	IEC 60250

Electrical Properties	Metric	English	Comments
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	250 V	250 V	d.a.m.; Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 280 Â°C	500 - 536 Â°F	
	270 Â°C	518 Â°F	for test specimens; ISO 294
Mold Temperature	80.0 - 100 Â°C	176 - 212 Â°F	
	90.0 Â°C	194 Â°F	for test specimens; ISO 294
Drying Temperature	120 Â°C	248 Â°F	
Dry Time	4 - 8 hour	4 - 8 hour	
Moisture Content	0.00 - 0.020 %	0.00 - 0.020 %	residual; Karl Fischer Test

Descriptive Properties	Value	Comments
Electrolytic Corrosion	IEC 60426	A 1
Halving Interval (Â°C)	10.2	IEC 60216-1, Tensile strength
	10.2	IEC 60216-1, Electric strength
	13.5	IEC 60216-1, Tensile impact strength
ISO Shortname	ISO 7792-1-PBT+PET, GHLMR, 09-160, GF45	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China