

## Lavergne VYTEEN PC/ABS 8515 Polycarbonate - Acrylonitrile Butadiene Styrene Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

### Material Notes:

Vyteen PC/ABS 8515 is an enhanced PC/ABS alloy with balanced impact/stiffness properties designed for injection molding applications. Features: -High resilience -Excellent processability -High deflection temperature Typical Applications: -Electronics - Appliances housing -Electrical components Information provided by Bieglo Gmbh for Lavergne Performance Compounds

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lavergne-VYTEEN-PCABS-8515-Polycarbonate-Acrylonitrile-Butadiene-Styrene-Alloy.php](http://www.lookpolymers.com/polymer_Lavergne-VYTEEN-PCABS-8515-Polycarbonate-Acrylonitrile-Butadiene-Styrene-Alloy.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ASTM D955
Melt Flow	10 g/10 min @Load 5.00 kg, Temperature 260 °C	10 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	50 mm/min; ASTM D638
Flexural Strength	100 MPa	14500 psi	1.3 mm/min; ASTM D790
Flexural Modulus	2.50 GPa	363 ksi	1.3 mm/min; ASTM D790
Izod Impact, Notched	5.50 J/cm @Temperature 23.0 °C	10.3 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	ASTM D648

Processing Properties	Metric	English	Comments
Feed Temperature	220 - 240 °C	428 - 464 °F	
Middle Barrel Temperature	240 - 260 °C	464 - 500 °F	
Front Barrel Temperature	250 - 270 °C	482 - 518 °F	
Nozzle Temperature	270 - 275 °C	518 - 527 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	60.0 - 90.0 Å°C	140 - 194 Å°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China