

Lehmann & Voss LUVOCOM[®] 1100-7721/WT9016 Polyether sulfone, unreinforced

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

Applications: Apparatus- and precision engineering, film- and photo industry, sporting- and leisure goods, medical- and electrical engineering, aircraft- and aerospace industry. High dimensionally stable precision parts, even at elevated temperatures and narrow tolerance range. Superheated steam sterilizable. Inherent flame resistance. High quality terminal bar, switches and plugs, relays, lamp reflectors, sterilizable medical equipment. Information provided by Lehmann & Voss & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1100-7721WT9016-Polyether-sulfone-unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	85.0 MPa	12300 psi	
Elongation at Yield	5.5 %	5.5 %	
	7.3 %	7.3 %	flexural
Modulus of Elasticity	3.00 GPa	435 ksi	
Flexural Strength	115 MPa	16700 psi	
Flexural Modulus	2.00 GPa	290 ksi	
Charpy Impact Unnotched	9.00 J/cm ^Â 2	42.8 ft-lb/in ^Â 2	flatwise; ISO 179 1fU
Charpy Impact, Notched	0.500 J/cm ^Â 2	2.38 ft-lb/in ^Â 2	ISO 179 1eA
Coefficient of Friction, Dynamic	0.34	0.34	
Coefficient of Friction, Static	0.28	0.28	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 Â°C	356 Â°F	
	220 Â°C	428 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	195 Â°C	383 Â°F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	350 Â°C	662 Â°F	mass temp
Nozzle Temperature	340 - 360 Â°C	644 - 680 Â°F	
Zone 1	355 - 375 Â°C	671 - 707 Â°F	
Zone 2	360 - 380 Â°C	680 - 716 Â°F	
Zone 3	350 - 370 Â°C	662 - 698 Â°F	
Mold Temperature	120 - 200 Â°C	248 - 392 Â°F	
Drying Temperature	150 Â°C @Time 10800 - 18000 sec	302 Â°F @Time 3.00 - 5.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	traffic white	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China