

Lehmann & Voss LUVOCOM[®] 1105-0918/BL PEEK, with glass fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Glass Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry.Strong, stiff parts.Chemical and hydrolysis resistance parts, non flammable.High dimensionally stable precision parts, high continuous use temperature.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-0918BL-PEEK-with-glass-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.57 g/cc	1.57 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	145 MPa	21000 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.5 %	2.5 %	flexural
Modulus of Elasticity	11.0 GPa	1600 ksi	
Flexural Strength	205 MPa	29700 psi	
Flexural Modulus	9.00 GPa	1310 ksi	
Charpy Impact Unnotched	3.50 J/cm ²	16.7 ft-lb/in ²	flatwise; ISO 179 1fU
	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Coefficient of Friction, Dynamic	0.32	0.32	
Coefficient of Friction, Static	0.30	0.30	

Thermal Properties	Metric	English	Comments
CTE, linear	22.0 Âµm/m-Â°C	12.2 Âµin/in-Â°F	DIN 53752
Thermal Conductivity	0.400 W/m-K	2.78 BTU-in/hr-ft ² - Â°F	DIN 52612
Maximum Service Temperature, Air	250 Â°C	482 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	315 Â°C	599 Â°F	
Vicat Softening Point	325 Â°C	617 Â°F	DIN ISO 306
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	traffic blue	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China