

Lehmann & Voss LUVOCOM[®] 1105-0950/RD PEEK, unreinforced

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry. Especially suitable for medical parts, superheated steam sterilizable, hydrolysis resistance High chemical resistance parts, non flammable. Inherent flame resistance. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-0950RD-PEEK-unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ISO 1183
Water Absorption	<= 0.50 %	<= 0.50 %	23Â°C/24h
Linear Mold Shrinkage	0.010 - 0.016 cm/cm	0.010 - 0.016 in/in	
Melt Flow	9.38 g/10 min @Load 5.00 kg, Temperature 380 Â°C	9.38 g/10 min @Load 11.0 lb, Temperature 716 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	95.0 MPa	13800 psi	
Elongation at Yield	5.0 %	5.0 %	
	6.0 %	6.0 %	flexural
Modulus of Elasticity	4.00 GPa	580 ksi	
Flexural Strength	150 MPa	21800 psi	
Flexural Modulus	3.00 GPa	435 ksi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr-ftÂ²- Â°F	DIN 52612
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	260 Â°C	500 Â°F	short term
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Insulation Resistance			

Electrical Properties	$\geq 1.00e+12$ ohm Metric	$\geq 1.00e+12$ ohm English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C @Time 21600 - 28800 sec	248 Â°F @Time 6.00 - 8.00 hour	or
	150 Â°C @Time 10800 - 21600 sec	302 Â°F @Time 3.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	brown	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China