

Lehmann & Voss LUVOCOM[®] 1105-7327 PEEK, with glass fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Glass Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry. Strong, stiff parts; impact resistance. Dynamic stressed parts at high movement velocity. Chemical and hydrolysis resistance parts, non flammable. High dimensionally stable precision parts, high continuous use temperature. Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-7327-PEEK-with-glass-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.82 g/cc	1.82 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	
Melt Flow	12.74 g/10 min @Load 5.00 kg, Temperature 380 Â°C	12.74 g/10 min @Load 11.0 lb, Temperature 716 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	160 MPa	23200 psi	
Elongation at Yield	1.3 %	1.3 %	
	2.2 %	2.2 %	flexural
Modulus of Elasticity	19.0 GPa	2760 ksi	
Flexural Strength	250 MPa	36300 psi	
Flexural Modulus	17.0 GPa	2470 ksi	
Charpy Impact Unnotched	4.00 J/cmÂ²	19.0 ft-lb/inÂ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	280 Â°C	536 Â°F	short term
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	natural color	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China