

Lehmann & Voss LUVOCOM[®] 1105-7914 PEEK, with carbon fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry.Strong, stiff parts.Dynamic stressed parts.High chemical resistance parts, hydrolysis resistance, non flammable.Antistatic.Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-7914-PEEK-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0080 cm/cm	0.0020 - 0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	160 MPa	23200 psi	
Elongation at Yield	3.5 %	3.5 %	
	4.3 %	4.3 %	flexural
Modulus of Elasticity	11.0 GPa	1600 ksi	
Flexural Strength	235 MPa	34100 psi	
Flexural Modulus	9.00 GPa	1310 ksi	
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	280 Â°C	536 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+10 ohm	<= 1.00e+10 ohm	
Insulation Resistance	<= 1.00e+10 ohm	<= 1.00e+10 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp

Processing Properties	Metric	English	Comments
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China