

## Lehmann & Voss LUVOCOM<sup>®</sup> 1105-8108 PEEK, with glass fiber, lubricant modified

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Glass Fiber Filled

### Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry.Strong, stiff parts.Chemical and hydrolysis resistance parts, non flammable.Improved friction and wear behaviour. Emergency running property.Low warpage.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-1105-8108-PEEK-with-glass-fiber-lubricant-modified.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105-8108-PEEK-with-glass-fiber-lubricant-modified.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0050 - 0.010 cm/cm	0.0050 - 0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	130 MPa	18900 psi	
Elongation at Yield	3.0 %	3.0 %	
	4.0 %	4.0 %	flexural
Modulus of Elasticity	7.50 GPa	1090 ksi	
Flexural Strength	185 MPa	26800 psi	
Flexural Modulus	6.50 GPa	943 ksi	
Charpy Impact Unnotched	4.60 J/cm <sup>2</sup>	21.9 ft-lb/in <sup>2</sup>	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	260 Â°C	500 Â°F	short term
Vicat Softening Point	305 Â°C	581 Â°F	DIN ISO 306
Flammability, UL94	V-0	V-0	not recognized by UL

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Insulation Resistance Electrical Properties	$\geq 1.00e+12$ ohm Metric	$\geq 1.00e+12$ ohm English	Comments
--	-------------------------------	--------------------------------	----------

Processing Properties	Metric	English	Comments
Processing Temperature	390 Å°C	734 Å°F	mass temp
Nozzle Temperature	360 - 380 Å°C	680 - 716 Å°F	
Zone 1	360 - 370 Å°C	680 - 698 Å°F	
Zone 2	380 - 390 Å°C	716 - 734 Å°F	
Zone 3	390 - 400 Å°C	734 - 752 Å°F	
Mold Temperature	170 - 200 Å°C	338 - 392 Å°F	
Drying Temperature	120 Å°C @Time 21600 - 28800 sec	248 Å°F @Time 6.00 - 8.00 hour	or
	150 Å°C @Time 10800 - 21600 sec	302 Å°F @Time 3.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	dark grey	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China