

Lehmann & Voss LUVOCOM[®] 1105/XCF/15 PEEK, with carbon fiber

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile machinery, medical- and precision engineering, aircraft industry. High-strength and high-stiff parts; low coefficient of expansion. Dynamic stressed parts at high movement velocity. Chemical and hydrolysis resistance parts, non flammable. Electrically conductive, suitable for continuous discharging of statically generated electricity. Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1105XCF15-PEEK-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	240 MPa	34800 psi	
Elongation at Yield	2.4 %	2.4 %	
	3.1 %	3.1 %	flexural
Modulus of Elasticity	16.0 GPa	2320 ksi	
Flexural Strength	345 MPa	50000 psi	
Flexural Modulus	14.0 GPa	2030 ksi	
Charpy Impact Unnotched	5.20 J/cm ²	24.7 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	300 Â°C	572 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1e+05	<= 1e+05	
Insulation Resistance	<= 100000 ohm	<= 100000 ohm	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 200 Â°C	338 - 392 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China