

Lehmann & Voss LUVOCOM[®] 1301-7661/RD PPS, linear, with glass fiber and PTFE

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Glass Fiber Filler

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.High continuous use and heat distortion temperature. Non flammable.Strong, stiff parts.Improved friction and wear behaviour. Emergency running property.High chemical resistance parts.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-7661RD-PPS-linear-with-glass-fiber-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.44 g/cc	1.44 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23 [°] C/24h
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	80.0 MPa	11600 psi	
Elongation at Yield	2.2 %	2.2 %	
	3.0 %	3.0 %	flexural
Modulus of Elasticity	5.00 GPa	725 ksi	
Flexural Strength	115 MPa	16700 psi	
Flexural Modulus	4.00 GPa	580 ksi	
Charpy Impact Unnotched	2.50 J/cm ²	11.9 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 [°] C	428 [°] F	
	240 [°] C	464 [°] F	short term
Deflection Temperature at 1.8 MPa (264 psi)	250 [°] C	482 [°] F	

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 340 Â°C	608 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C	122 - 194 Â°F	
	@Time >=14400 sec	@Time >=4.00 hour	
	100 - 140 Â°C	212 - 284 Â°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China