

## Lehmann & Voss LUVOCOM<sup>®</sup> 1301-8077 PPS, linear, with carbon fiber

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Carbon Fiber Filler

### Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering. Electrically conductive, suitable for continuous discharging of statically generated electricity. Strong, stiff parts. Reduced moment of inertia compared with metal parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-1301-8077-PPS-linear-with-carbon-fiber.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-8077-PPS-linear-with-carbon-fiber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	130 MPa	18900 psi	
Elongation at Yield	1.4 %	1.4 %	
	1.8 %	1.8 %	flexural
Modulus of Elasticity	14.0 GPa	2030 ksi	
Flexural Strength	190 MPa	27600 psi	
Flexural Modulus	12.0 GPa	1740 ksi	
Charpy Impact Unnotched	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 Â°C	428 Â°F	
	240 Â°C	464 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	220 Â°C	428 Â°F	

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 10 ohm	<= 10 ohm	
Insulation Resistance	<= 10 ohm	<= 10 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 340 Â°C	608 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C	122 - 194 Â°F	
	@Time >=14400 sec	@Time >=4.00 hour	
	100 - 140 Â°C	212 - 284 Â°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China