

Lehmann & Voss LUVOCOM[®] 1301-8306 PPS, linear, with carbon fiber, lubricant modified

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Carbon Fiber Filler

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.Strong, stiff parts.Improved friction and wear behaviour. Emergency running property.Inherent flame resistance.Gear parts for automotive appliances, control disks, cams, sliding elements.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-8306-PPS-linear-with-carbon-fiber-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.96 g/cc	1.96 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23 [°] C/24h
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	105 MPa	15200 psi	
Elongation at Yield	0.50 %	0.50 %	
	0.70 %	0.70 %	flexural
Modulus of Elasticity	34.0 GPa	4930 ksi	
Flexural Strength	145 MPa	21000 psi	
Flexural Modulus	27.0 GPa	3920 ksi	
Charpy Impact Unnotched	1.00 J/cm ²	4.76 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 [°] C	428 [°] F	
	240 [°] C	464 [°] F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	
Insulation Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Nozzle Temperature	320 - 340 Â°C	608 - 644 Â°F	
Zone 1	300 - 320 Â°C	572 - 608 Â°F	
Zone 2	310 - 330 Â°C	590 - 626 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	150 - 180 Â°C	302 - 356 Â°F	
Drying Temperature	50.0 - 90.0 Â°C	122 - 194 Â°F	
	@Time >=14400 sec	@Time >=4.00 hour	
	100 - 140 Â°C	212 - 284 Â°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China