

Lehmann & Voss LUVOCOM[®] 1800-7806 PET, with PTFE

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Improved friction and wear behaviour. Emergency running property. Isotropic shrinkage characteristics. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1800-7806-PET-with-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc	1.55 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23Â°C/24h
Linear Mold Shrinkage	0.015 - 0.020 cm/cm	0.015 - 0.020 in/in	
Melt Flow	<= 31 g/10 min @Load 2.16 kg, Temperature 250 Â°C	<= 31 g/10 min @Load 4.76 lb, Temperature 482 Â°F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 Â°C	212 Â°F	
	180 Â°C	356 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	280 Â°C	536 Â°F	mass temp
Nozzle Temperature	265 - 275 Â°C	509 - 527 Â°F	
Zone 1	285 - 295 Â°C	545 - 563 Â°F	
Zone 2	270 - 280 Â°C	518 - 536 Â°F	
Zone 3	265 - 275 Â°C	509 - 527 Â°F	
Mold Temperature	60.0 - 120 Â°C	140 - 248 Â°F	
Drying Temperature	80.0 Â°C @Time 21600 - 28800	176 Â°F	

Processing Properties	^{sec} Metric	^{@Time 6.00 - 8.00 hour} English	Comments
	120 Å°C	248 Å°F	Dehumidifying dryer
	@Time 7200 - 18000 sec	@Time 2.00 - 5.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (white)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China