

Lehmann & Voss LUVOCOM[®] 1850-7942 PBT, with PTFE, lubricant modified

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), PTFE Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Improved friction and wear behaviour. Emergency running property. Isotropic shrinkage characteristics. Control disks, cams, sliding elements and other duty parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1850-7942-PBT-with-PTFE-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23Â°C/24h
Linear Mold Shrinkage	0.014 - 0.020 cm/cm	0.014 - 0.020 in/in	
Melt Flow	20.85 g/10 min @Load 2.16 kg, Temperature 250 Â°C	20.85 g/10 min @Load 4.76 lb, Temperature 482 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	40.0 MPa	5800 psi	
Elongation at Yield	4.0 %	4.0 %	
	5.5 %	5.5 %	flexural
Modulus of Elasticity	2.00 GPa	290 ksi	
Flexural Strength	60.0 MPa	8700 psi	
Flexural Modulus	2.00 GPa	290 ksi	
Charpy Impact Unnotched	3.50 J/cmÂ²	16.7 ft-lb/inÂ²	flatwise; ISO 179 1fU
Coefficient of Friction, Dynamic	0.15	0.15	
Coefficient of Friction, Static	0.11	0.11	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 Â°C	266 Â°F	
	150 Â°C	302 Â°F	short term

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Processing Temperature	250 Â°C	482 Â°F	mass temp
Nozzle Temperature	250 - 265 Â°C	482 - 509 Â°F	
Zone 1	240 - 260 Â°C	464 - 500 Â°F	
Zone 2	260 - 280 Â°C	500 - 536 Â°F	
Zone 3	250 - 270 Â°C	482 - 518 Â°F	
Mold Temperature	60.0 - 120 Â°C	140 - 248 Â°F	
Drying Temperature	80.0 Â°C	176 Â°F	Vacuum Dryer
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	120 Â°C	248 Â°F	Dehumidifying dryer
	@Time 14400 - 21600 sec	@Time 4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	natural color (white)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China