

Lehmann & Voss LUVOCOM[®] 19-7278 Polyamide 46, with carbon fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. High-strength and high-stiff parts; low coefficient of expansion. Reduced moment of inertia compared with metal parts. Electrically conductive, suitable for continuous discharging of statically generated electricity. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-19-7278-Polyamide-46-with-carbon-fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	230 MPa	33400 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.6 %	2.6 %	flexural
Modulus of Elasticity	16.0 GPa	2320 ksi	
Flexural Strength	325 MPa	47100 psi	
Flexural Modulus	14.0 GPa	2030 ksi	
Charpy Impact Unnotched	5.50 J/cm ²	26.2 ft-lb/in ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 Â°C	302 Â°F	
	160 Â°C	320 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	>= 290 Â°C	>= 554 Â°F	

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 10000 ohm	<= 10000 ohm	

Insulation Resistance Electrical Properties	≤ 10000 ohm Metric	≤ 10000 ohm English	Comments
--	----------------------------	-----------------------------	----------

Processing Properties	Metric	English	Comments
Processing Temperature	310 Â°C	590 Â°F	mass temp
Nozzle Temperature	280 - 330 Â°C	536 - 626 Â°F	
Zone 1	285 - 315 Â°C	545 - 599 Â°F	
Zone 2	305 - 315 Â°C	581 - 599 Â°F	
Zone 3	305 - 315 Â°C	581 - 599 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	80.0 Â°C @Time 7200 - 43200 sec	176 Â°F @Time 2.00 - 12.0 hour	Vacuum Dryer
	80.0 Â°C @Time 7200 - 28800 sec	176 Â°F @Time 2.00 - 8.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China