

Lehmann & Voss LUVOCOM[®] 19-7660 Polyamide 46, with glass fiber, PTFE, lubricant modified

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Lubricated + Glass Fiber Reinforced

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts. Highly dimensionally stable at elevated temperatures. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-19-7660-Polyamide-46-with-glass-fiber-PTFE-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc	1.55 g/cc	ISO 1183
Water Absorption	1.5 %	1.5 %	23 [°] C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	150 MPa	21800 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.6 %	2.6 %	flexural
Modulus of Elasticity	11.0 GPa	1600 ksi	
Flexural Strength	215 MPa	31200 psi	
Flexural Modulus	9.00 GPa	1310 ksi	
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 [°] C	302 [°] F	
	240 [°] C	464 [°] F	short term
Deflection Temperature at 1.8 MPa (264 psi)	285 [°] C	545 [°] F	

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+9 ohm	>= 1.00e+9 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	310 Â°C	590 Â°F	mass temp
Nozzle Temperature	280 - 330 Â°C	536 - 626 Â°F	
Zone 1	285 - 315 Â°C	545 - 599 Â°F	
Zone 2	305 - 315 Â°C	581 - 599 Â°F	
Zone 3	305 - 315 Â°C	581 - 599 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	80.0 Â°C @Time 7200 - 43200 sec	176 Â°F @Time 2.00 - 12.0 hour	Vacuum Dryer
	80.0 Â°C @Time 7200 - 28800 sec	176 Â°F @Time 2.00 - 8.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China