

Lehmann & Voss LUVOCOM[®] 19-7744 Polyamide 46, with aramid reinforcement and PTFE

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Good friction and wear behaviour especially at increased temperatures. Emergency running property. Bearings, sleeves, sliding elements, control disks, gear wheels, duty parts in switches. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-19-7744-Polyamide-46-with-aramid-reinforcement-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.013 - 0.020 cm/cm	0.013 - 0.020 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	65.0 MPa	9430 psi	
Elongation at Yield	5.0 %	5.0 %	
	6.5 %	6.5 %	flexural
Modulus of Elasticity	2.90 GPa	421 ksi	
Flexural Strength	95.0 MPa	13800 psi	
Flexural Modulus	2.60 GPa	377 ksi	
Charpy Impact Unnotched	3.20 J/cm ²	15.2 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 Â°C	302 Â°F	
	160 Â°C	320 Â°F	short term

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	310 Â°C	590 Â°F	mass temp

Processing Properties	Metric	English	Comments
Zone 1	285 - 315 Â°C	545 - 599 Â°F	
Zone 2	305 - 315 Â°C	581 - 599 Â°F	
Zone 3	305 - 315 Â°C	581 - 599 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	80.0 Â°C @Time 7200 - 28800 sec	176 Â°F @Time 2.00 - 8.00 hour	Dehumidifying dryer
	80.0 Â°C @Time 7200 - 43200 sec	176 Â°F @Time 2.00 - 12.0 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	natural color (beige)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China