

Lehmann & Voss LUVOCOM[®] 19-8094 Polyamide 46, with carbon fiber and PTFE

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts. Reduced moment of inertia compared with metal parts. Electrically conductive, suitable for continuous discharging of statically generated electricity. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-19-8094-Polyamide-46-with-carbon-fiber-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 300 Â°C	12 g/10 min @Load 4.76 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	165 MPa	23900 psi	
Elongation at Yield	2.2 %	2.2 %	
	2.6 %	2.6 %	flexural
Modulus of Elasticity	11.0 GPa	1600 ksi	
Flexural Strength	235 MPa	34100 psi	
Flexural Modulus	9.00 GPa	1310 ksi	
Charpy Impact Unnotched	4.00 J/cmÂ²	19.0 ft-lb/inÂ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.500 J/cmÂ²	2.38 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 Â°C	302 Â°F	
	160 Â°C	320 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	>= 290 Â°C	>= 554 Â°F	

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	
Insulation Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	310 Â°C	590 Â°F	mass temp
Nozzle Temperature	280 - 330 Â°C	536 - 626 Â°F	
Zone 1	285 - 315 Â°C	545 - 599 Â°F	
Zone 2	305 - 315 Â°C	581 - 599 Â°F	
Zone 3	305 - 315 Â°C	581 - 599 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	80.0 Â°C @Time 7200 - 43200 sec	176 Â°F @Time 2.00 - 12.0 hour	Vacuum Dryer
	80.0 Â°C @Time 7200 - 28800 sec	176 Â°F @Time 2.00 - 8.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China