

Lehmann & Voss LUVOCOM[®] 20-0664 Polyphthalamide, with PTFE, lubricant modified

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Improved friction and wear behaviour. Emergency running property. Low influence from moisture and temperature to measures and electrical properties, compared with PA66. Suitable for metall inserts. Bearings, sleeves, sliding elements, control disks, gear wheels, duty parts in switches. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-20-0664-Polyphthalamide-with-PTFE-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23 [°] C/24h
Linear Mold Shrinkage	0.0080 - 0.011 cm/cm	0.0080 - 0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	80.0 MPa	11600 psi	
Elongation at Yield	3.0 %	3.0 %	
	3.5 %	3.5 %	flexural
Modulus of Elasticity	4.00 GPa	580 ksi	
Flexural Strength	105 MPa	15200 psi	
Flexural Modulus	3.50 GPa	508 ksi	
Charpy Impact Unnotched	5.70 J/cm ²	27.1 ft-lb/in ²	flatwise; ISO 179 1fU
	5.20 J/cm ²	24.7 ft-lb/in ²	ISO 179
	@Temperature -30.0 [°] C	@Temperature -22.0 [°] F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	165 [°] C	329 [°] F	
	195 [°] C	383 [°] F	short term
Deflection Temperature at 1.8 MPa (264 psi)	115 [°] C	239 [°] F	

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 330 Â°C	608 - 626 Â°F	
Zone 1	320 - 340 Â°C	608 - 644 Â°F	
Zone 2	320 - 345 Â°C	608 - 653 Â°F	
Zone 3	325 - 350 Â°C	617 - 662 Â°F	
Mold Temperature	135 - 160 Â°C	275 - 320 Â°F	
Drying Temperature	80.0 Â°C @Time 57600 sec	176 Â°F @Time 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 18000 sec	221 Â°F @Time 4.00 - 5.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China