

## Lehmann & Voss LUVOCOM<sup>®</sup> 20-8112 Polyphthalamide, with carbon fiber, lubricant modified

Category : Polymer , Thermoplastic , Polyphthalamide (PPA) , Polyphthalamide (PPA), Carbon Fiber Filled

### Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts. Dynamic stressed parts at high movement velocity. Improved friction and wear behaviour. Emergency running property. Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-20-8112-Polyphthalamide-with-carbon-fiber-lubricant-modified.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-20-8112-Polyphthalamide-with-carbon-fiber-lubricant-modified.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23 <sup>°</sup> C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	145 MPa	21000 psi	
Elongation at Yield	1.4 %	1.4 %	
	2.0 %	2.0 %	flexural
Modulus of Elasticity	13.0 GPa	1890 ksi	
Flexural Strength	210 MPa	30500 psi	
Flexural Modulus	11.0 GPa	1600 ksi	
Charpy Impact Unnotched	2.20 J/cm <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	165 <sup>°</sup> C	329 <sup>°</sup> F	
	195 <sup>°</sup> C	383 <sup>°</sup> F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+9 ohm	<= 1.00e+9 ohm	
Insulation Resistance	<= 1.00e+9 ohm	<= 1.00e+9 ohm	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Nozzle Temperature	320 - 330 Â°C	608 - 626 Â°F	
Zone 1	320 - 340 Â°C	608 - 644 Â°F	
Zone 2	320 - 345 Â°C	608 - 653 Â°F	
Zone 3	325 - 350 Â°C	617 - 662 Â°F	
Mold Temperature	135 - 160 Â°C	275 - 320 Â°F	
Drying Temperature	80.0 Â°C @Time 57600 sec	176 Â°F @Time 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 18000 sec	221 Â°F @Time 4.00 - 5.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	dark grey	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China