

## Lehmann & Voss LUVOCOM<sup>®</sup> 50-7154/V0 Polycarbonate, with carbon fiber, low-warpage

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon Fiber Reinforced

### Material Notes:

Applications: Data processing machinery, precision engineering, film and photo industry, sporting and leisure goods, medical engineering. Strong, stiff parts. Reduced moment of inertia compared with metal parts. Electrically conductive, suitable for continuous discharging of statically generated electricity. High dimensionally stable precision parts with low warpage and narrow tolerance range. Body and duty parts in office equipment, gear wheels, grippers. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-50-7154V0-Polycarbonate-with-carbon-fiber-low-warpage.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-50-7154V0-Polycarbonate-with-carbon-fiber-low-warpage.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	
Melt Flow	13.1 g/10 min @Load 1.20 kg, Temperature 300 Â°C	13.1 g/10 min @Load 2.65 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	105 MPa	15200 psi	
Elongation at Yield	2.8 %	2.8 %	
	3.2 %	3.2 %	flexural
Modulus of Elasticity	9.00 GPa	1310 ksi	
Flexural Strength	145 MPa	21000 psi	
Flexural Modulus	7.00 GPa	1020 ksi	
Charpy Impact Unnotched	3.50 J/cmÂ²	16.7 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 Â°C	266 Â°F	
	150 Â°C	302 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	145 Â°C	293 Â°F	
Vicat Softening Point	160 Â°C	320 Â°F	DIN ISO 306

Thermal Properties	Metric	English	Comments
Flammability, UL 94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 10000 ohm	<= 10000 ohm	
Insulation Resistance	<= 10000 ohm	<= 10000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	295 Â°C	563 Â°F	mass temp
Nozzle Temperature	290 - 310 Â°C	554 - 590 Â°F	
Zone 1	280 - 300 Â°C	536 - 572 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	300 - 320 Â°C	572 - 608 Â°F	
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	
Drying Temperature	120 Â°C @Time 14400 - 21600 sec	248 Â°F @Time 4.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China