

Lehmann & Voss LUVOCOM[®] 50-8479/BL-1 Polycarbonate, unreinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Applications: Data processing machinery, precision engineering, film and photo industry, sporting and leisure goods, medical engineering. Isotropic shrinkage characteristics. Reduced moment of inertia compared with metal parts. High dimensionally stable precision parts. Handles, levers, rollers, body parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-50-8479BL-1-Polycarbonate-unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23Â°C/24h
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	
Melt Flow	24.48 g/10 min @Load 1.20 kg, Temperature 300 Â°C	24.48 g/10 min @Load 2.65 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	55.0 MPa	7980 psi	
Elongation at Yield	5.0 %	5.0 %	
	6.5 %	6.5 %	flexural
Modulus of Elasticity	2.50 GPa	363 ksi	
Flexural Strength	80.0 MPa	11600 psi	
Flexural Modulus	2.00 GPa	290 ksi	
Charpy Impact Unnotched	11.0 J/cmÂ²	52.3 ft-lb/inÂ²	flatwise; ISO 179 1fU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 Â°C	266 Â°F	
	150 Â°C	302 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	295 Â°C	563 Â°F	mass temp
Nozzle Temperature	290 - 310 Â°C	554 - 590 Â°F	
Zone 1	280 - 300 Â°C	536 - 572 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	300 - 320 Â°C	572 - 608 Â°F	
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	
Drying Temperature	120 Â°C @Time 14400 - 21600 sec	248 Â°F @Time 4.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	blue	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China