

## Lehmann & Voss LUVOCOM® 50/GF/20/TF/10/BK Polycarbonate, with glass fiber and PTFE

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Glass + PTFE Filled

### Material Notes:

Applications: Data processing machinery, precision engineering, film and photo industry, sporting and leisure goods, medical engineering. High-strength and high-stiff parts; low coefficient of expansion. Reduced moment of inertia compared with metal parts. Improved friction and wear behaviour. Emergency running property. High dimensionally stable precision parts, even at elevated temperatures and narrow tolerance range. Body and duty parts in office equipment, gear wheels, grippers. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-50GF20TF10BK-Polycarbonate-with-glass-fiber-and-PTFE.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-50GF20TF10BK-Polycarbonate-with-glass-fiber-and-PTFE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ISO 1183
Water Absorption	<= 0.20 %	<= 0.20 %	23°C/24h
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	95.0 MPa	13800 psi	
Elongation at Yield	3.0 %	3.0 %	
	3.5 %	3.5 %	flexural
Modulus of Elasticity	5.50 GPa	798 ksi	
Flexural Strength	140 MPa	20300 psi	
Flexural Modulus	5.00 GPa	725 ksi	
Charpy Impact Unnotched	2.70 J/cm <sup>2</sup>	12.8 ft-lb/in <sup>2</sup>	edgewise; ISO 179 1eU
	2.20 J/cm <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Coefficient of Friction, Dynamic	0.23	0.23	
Coefficient of Friction, Static	0.18	0.18	

Thermal Properties	Metric	English	Comments
CTE, linear	32.0 µm/m-°C	17.8 µin/in-°F	DIN 53752
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft <sup>2</sup> -°F	DIN 52612

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
	150 °C	302 °F	short term
Vicat Softening Point	160 °C	320 °F	DIN ISO 306
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	295 °C	563 °F	mass temp
Nozzle Temperature	290 - 310 °C	554 - 590 °F	
Zone 1	280 - 300 °C	536 - 572 °F	
Zone 2	290 - 310 °C	554 - 590 °F	
Zone 3	300 - 320 °C	572 - 608 °F	
Mold Temperature	80.0 - 120 °C	176 - 248 °F	
Drying Temperature	120 °C @Time 14400 - 21600 sec	248 °F @Time 4.00 - 6.00 hour	Dehumidifying dryer

Descriptive Properties	Value	Comments
Color	black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China