

Lehmann & Voss LUVOCOM[®] 80-8082 Polyacetal-copolymer, with carbon fiber, PTFE, lubricant modified

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts; low thermal coefficient of expansion. Electrically conductive, suitable for continuous discharging of statically generated electricity. High dimensionally stable precision parts. Transporting equipment for electrically sensible goods. No change of electric potential at bearings in case of separation of charge caused by transport and guiding of paper and foil. No mass temperature above 215[°]C! Ventilation of machinery is recommended. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-80-8082-Polyacetal-copolymer-with-carbon-fiber-PTFE-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.46 g/cc	1.46 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	23 [°] C/24h
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	115 MPa	16700 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.8 %	2.8 %	flexural
Modulus of Elasticity	14.0 GPa	2030 ksi	
Flexural Strength	170 MPa	24700 psi	
Flexural Modulus	12.0 GPa	1740 ksi	
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 [°] C	212 [°] F	
	120 [°] C	248 [°] F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 100 ohm	<= 100 ohm	
Insulation Resistance	<= 100 ohm	<= 100 ohm	

Electrical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	200 Â°C	392 Â°F	mass temp
Nozzle Temperature	175 - 200 Â°C	347 - 392 Â°F	
Zone 1	175 - 190 Â°C	347 - 374 Â°F	
Zone 2	185 - 205 Â°C	365 - 401 Â°F	
Zone 3	180 - 200 Â°C	356 - 392 Â°F	
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	
Drying Temperature	75.0 Â°C @Time 7200 - 28800 sec	167 Â°F @Time 2.00 - 8.00 hour	Dehumidifying dryer
	120 Â°C @Time 7200 - 14400 sec	248 Â°F @Time 2.00 - 4.00 hour	Air-Circulation Dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China