

Lehmann & Voss LUVOCOM[®] GS-H/2 Polyamide 66, lubricant modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Emergency running property. Isotropic shrinkage characteristics. Control disks, cams, sliding elements and other duty parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-GS-H2-Polyamide-66-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.010 - 0.015 cm/cm	0.010 - 0.015 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	86.0 MPa	12500 psi	
Elongation at Yield	5.0 %	5.0 %	
Modulus of Elasticity	3.00 GPa	435 ksi	
Flexural Strength	130 MPa	18900 psi	
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	flatwise; ISO 179 1fU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 Â°C	194 Â°F	
	110 Â°C	230 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 Â°C	554 Â°F	mass temp
Nozzle Temperature	280 - 300 Â°C	536 - 572 Â°F	
Zone 1	290 - 310 Â°C	554 - 590 Â°F	

Processing Properties	Metric	English	Comments
Zone 3	290 - 310 Â°C	554 - 590 Â°F	
Mold Temperature	90.0 - 120 Â°C	194 - 248 Â°F	
Drying Temperature	75.0 Â°C @Time 21600 - 57600 sec	167 Â°F @Time 6.00 - 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 21600 sec	221 Â°F @Time 4.00 - 6.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China